



# CERTIFICATE OF ACCREDITATION



## Froehling & Robertson, Incorporated

in

**Fayetteville, North Carolina, USA**

has demonstrated proficiency for the testing of construction materials and has conformed to the requirements established in AASHTO R 18 and the AASHTO Accreditation policies established by the AASHTO Committee on Materials and Pavements.

The scope of accreditation can be viewed on the Directory of AASHTO Accredited Laboratories ([aashtoresource.org](http://aashtoresource.org)).



---

Jim Tymon,  
AASHTO Executive Director



---

Matt Linneman  
AASHTO COMP Chair



## SCOPE OF AASHTO ACCREDITATION FOR:

Froehling & Robertson, Incorporated  
in Fayetteville, North Carolina, USA

## Quality Management System

### Standard:

### Accredited Since:

R18	Establishing and Implementing a Quality System for Construction Materials Testing Laboratories	01/20/2026
C1077 (Concrete)	Laboratories Testing Concrete and Concrete Aggregates	01/20/2026
E329 (Concrete)	Standard Specification for Agencies Engaged in the Testing and/or Inspection of Materials Used in Construction	01/20/2026



# SCOPE OF AASHTO ACCREDITATION FOR:

Froehling & Robertson, Incorporated  
in Fayetteville, North Carolina, USA

## Concrete

**Standard:****Accredited Since:**

C31 (Beams)	Making and Curing Concrete Test Specimens in the Field	01/20/2026
C31 (Cylinders)	Making and Curing Concrete Test Specimens in the Field	01/20/2026
C39	Compressive Strength of Cylindrical Concrete Specimens	01/20/2026
C78	Flexural Strength of Concrete (Using Simple Beam with Third-Point Loading)	01/20/2026
C138	Density (Unit Weight), Yield, and Air Content of Concrete	01/20/2026
C143	Slump of Hydraulic Cement Concrete	01/20/2026
C172	Sampling Freshly Mixed Concrete	01/20/2026
C173	Air Content of Freshly Mixed Concrete by the Volumetric Method	01/20/2026
C231	Air Content of Freshly Mixed Concrete by the Pressure Method	01/20/2026
C511	Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the testing of Hydraulic Cements and Concretes	01/20/2026
C617 (7000 psi and below)	Capping Cylindrical Concrete Specimens	01/20/2026
C1064	Temperature of Freshly Mixed Portland Cement Concrete	01/20/2026
C1231 (7000 psi and below)	Use of Unbonded Caps in Determination of Compressive Strength of Hardened Concrete Cylinders	01/20/2026