

Laboratory Assessment Preparation List

General Assessment Guidance: This document is intended to provide guidance for laboratories preparing for an AASHTO re:source On-Site Laboratory Assessment, specifically with regard to the preparation and availability of materials required for demonstration of the test method(s). Preparing for the assessment will improve the efficiency, productivity, and benefit of the assessment for the laboratory.

This document does not address all of the apparatus and procedural requirements which may be evaluated during the assessment. Please consult the applicable AASHTO or ASTM standard for specific requirements. The laboratory may elect to demonstrate the AASHTO, ASTM, or both versions of the test method. The laboratory should be prepared to present required apparatus and to perform the test method in its entirety. Please contact us at (240) 436-4900 if your laboratory has additional questions with regard to preparing for the On-Site Assessment.

<u>AASHTO</u>	<u>ASTM</u>	Asphalt Cement Assessment Preparation
R28	D6521	Have an RTFO-conditioned sample ready to load into the PAV. If you are scheduled for a one-day assessment, please have a sample ready to depressurize in the morning and the assessor will watch the sample being loaded in the afternoon. Be able to obtain the temperature and pressure records for the test.
R29		Have records of determining the grade of an unknown binder and/or records of verifying the nominal grade of an asphalt binder. Be prepared to discuss the use of the reports/records used to determine grading.
T44	D2042	Have an asphalt sample ready to pour and the vacuum system apparatus assembled.
T48	D92	Have an asphalt sample ready to pour and the flash tester assembled. Be prepared to maintain the proper temperature rates and have a method for checking atmospheric pressure available. Please have the certified reference material(s) and associated documents available for review.
T49	D5	Have an asphalt sample ready to pour and the bath at temperature. Be able to explain additional procedures followed for penetration values over 200.
T50	D139	Have an asphalt sample ready to pour and baths at temperature. Have float depth immersion records available for review.
T51	D113	Have an asphalt sample ready to pour and baths at temperature.
T53	D36	Have an asphalt sample ready to pour. Be prepared to maintain the proper temperature rates.
T55	D95	Have an asphalt sample ready to pour and the apparatus assembled. Be prepared to maintain drip rates.
T78	D402	Have a cut-back sample ready to pour and the apparatus assembled. Be prepared to maintain drip rates.
T79	D3143	Have an asphalt sample ready to pour and the flash tester assembled. Be able to demonstrate the test with the proper temperature rates and have a method for checking atmospheric pressure.
<u>T111</u>	D8078	Have an asphalt sample ready to pour and the furnace at temperature.
T179	D1754	Have an asphalt sample ready to pour and the oven at temperature. Please note the assessor will have to shut the oven off to measure inside dimensions: please plan your testing schedule accordingly.
T201 T202	D2170 D2171	Have an asphalt sample ready to pour and both the bath and oven at temperature. Please select an appropriate viscometer and have the calibration factor available for review.

AASHTO	ASTM	Asphalt Cement Assessment Preparation (Continued)
T228	D70	Have an asphalt sample ready to pour and the bath at temperature.
T240	D2872	Have an asphalt sample ready to pour and the oven at temperature. Please note the assessor will have to shut the oven off to measure inside dimensions; please plan your testing schedule accordingly.
T295	D3142	Have an asphalt sample ready to pour and the appropriate hydrometer selected for the test.
T300		Have an asphalt sample ready to pour and baths at temperature.
T301	D6084	Have an asphalt sample ready to pour and baths at temperature.
T313	D6648	Have a PAV-aged sample ready to pour and the bath at temperature. Be prepared to demonstrate verification of the apparatus and have the appropriate records required for verification available. Please be able to print the test results at the completion of testing.
T315	D7175	Have an asphalt sample ready to pour. Please note that demonstration using both the 25 mm plate and the 8 mm plate are required. Choose either an un-aged binder sample or an RTFO-aged binder sample for 25 mm plate demonstration. Please have all calibration records, the reference thermometer, portable thermometer, and all certified reference fluids available for review. Be prepared to print the test results at the completion of testing.
T316	D4402	Have an asphalt sample ready to pour and the machine and apparatus preheated. Be able to present the certified reference fluid used for calibration.
T350	D7405	Have an RTFO-conditioned sample ready to pour if the system is unable to transition from DSR into MSCR. Please be able to print the test results at the completion of testing.
	D243	Have a residue sample ready to pour and the bath at temperature.
	D5801	Have an asphalt sample ready to pour and the bath at temperature. Please be able to print the test results at the completion of testing or have one available to review.
	D7553	Have an asphalt sample ready to pour and the vacuum system apparatus assembled.
	D7643	Have records of determining the continuous grade of an unknown binder and/or records of verifying the continuous grade of an asphalt binder. Be prepared to discuss the use of the records/reports to determine grading.